220002289339

中国认可
国际互认
检测
TESTING
CNASL1417

报告编号Report Number：2025W12239FY

验证码Verification Code： B60TRJ

检 验 报 告

Testing Report

受 检 单 位 青岛望展新材料科技有限公司
Submittal Company Qingdao Looking Forward New Material Technology Co., Ltd.

样 品 名 称 水泥毯(Concrete Canvas)
Sample Name

委 托 单 位 青岛望展新材料科技有限公司
Entrusting Company Qingdao Looking Forward New Material Technology Co., Ltd.

检 验 类 别 委托
Testing Classification Commission

中国建材检验认证集团苏州有限公司
China Building Material Test & Certification Group Suzhou Co., Ltd.
国家防水与节水材料产品质量检验检测中心
Inspection & Testing Center for National Waterproof and Water-saving Material Product Quality
国家建筑材料工业建筑防水材料产品质量监督检验测试中心
Supervision & Testing Center of State Building Materials Industry for Building Waterproofing Materials Product Quality

国检集团

二〇二六年一月十九日
Jan.19, 2026

中国建材检验认证集团苏州有限公司
China Building Material Test & Certification Group Suzhou Co. Ltd.

检 验 报 告
Testing Report

报告编号: 2025W12239FY
Report Number

样品名称 Sample Name	水泥毯（Concrete Canvas）	规格类型 Specification & Model	12mm
受检单位 Submittal Company	青岛望展新材料科技有限公司 Qingdao Looking Forward New Material Technology Co., Ltd.	配 合 比 Mixture Ratio	/
生产单位 Manufacturer	青岛望展新材料科技有限公司 Qingdao Looking Forward New Material Technology Co., Ltd.	商 标 Trademark	望展 Looking forward
委托单位 Entrusting Company	青岛望展新材料科技有限公司 Qingdao Looking Forward New Material Technology Co., Ltd.	生产日期 Production Date	20250916
委托单位地址 Entrusting Company Address	山东省德州市陵城区安德街道武佑街与安泰路路口北88米路东 88 meters north of the intersection of Wuyou Street and Antai Road, Ande Sub-district, Lingcheng District, Dezhou City, Shandong Province	批 号 Batch Number	/
以上信息及样品由委托单位提供及确认，本公司不承担证实委托单位提供信息的准确性、适当性和完整性的责任。 The above information and sample were provided and confirmed by the entrusting company. Our company does not assume responsibility for verifying the accuracy, appropriateness, or completeness of the information provided by the entrusting company.			
检验类别 Testing Classification	委托 Commission	到样日期 Received Date	2025-12-10
样品状态 Sample State	布状物，完好 Fabric, in good condition	检验日期 Testing Date	2025-12-10～2026-01-09
样品数量 Sample Quantity	$2m^2$	检验地点 Testing Address	和顺路1号 No.1 Heshun Road
判定依据 Judgement Criterion	/		
检验项目及检测依据 Testing Item & Specification	详见第2页， See Page 2 for details.		
检验结论 Testing Conclusion	样品经检验，检验结果见第3页。以下空白 The sample has been tested and the test results are shown on page 3. The following is blank. 检验单位章 Testing center seal 签发日期：二〇二六年一月十九日 Sign and issue date Jan. 19, 2026		
备注 Comment	（此处空白This field is blank.）		

批准：
Approved by

审核：
Examined by

主检：
Inspected by

检 验 报 告
Testing Report

报告编号: 2025W12239FY
Report Number

序号 No.	检验项目 Testing Item	检测依据 Testing Specification
1	厚度 Thickness	GB/T 13761.1-2022《土工合成材料 规定压力下厚度的测定 第1部分：单层产品》 GB/T 13761.1-2022 Geosynthetics-Determination of thickness at specified pressures-Part 1: Single layers
2	单位面积质量 Unit area mass	GB/T 13762-2009《土工合成材料 土工布及土工布有关产品单位面积质量的测定方法》 GB/T 13762-2009 Geosynthetics-Test method for the determination of mass per unit area of geotextiles and geotextile-Related products
3	抗折强度 Flexural strength	GB/T 7019-2024《纤维水泥制品试验方法》5.7 GB/T 7019-2024 Test methods for fiber cement products 5.7
4	抗冲击性 Impact resistance	GB/T 7019-2024《纤维水泥制品试验方法》5.9 GB/T 7019-2024 Test methods for fiber cement products 5.9
5	不透水性 Water impermeability	GB/T 7019-2024《纤维水泥制品试验方法》5.4 GB/T 7019-2024 Test methods for fiber cement products 5.4
	本页以下空白 The following is blank in this page.	
备注 Comment	（此处空白This field is blank.）.	

检 验 报 告
Testing Report

报告编号: 2025W12239FY
Report Number

序号 No.	检验项目 Testing Item	试验条件 Testing Condition	检验结果 Testing Result
1	厚度，mm Thickness	（20±2）℃，相对湿度（65±4）% （20±2）℃，Relative humidity（65±4）%	12.33
2	单位面积质量，kg/m^2 Unit area mass	（20±2）℃，相对湿度（65±4）% （20±2）℃，Relative humidity（65±4）%	15
3	抗折强度，MPa Flexural strength	（23±2）℃，相对湿度（50±5）% （23±2）℃，Relative humidity（50±5）% 正方形试件 Square specimens 加荷时间（10～30）s Loading time: (10～30) s	9.8
4	抗冲击性 Impact resistance	（23±2）℃，相对湿度（50±5）% （23±2）℃，Relative humidity（50±5）% 落球法 Drop ball method 冲击高度110cm Impact height: 110 cm	无裂纹 No cracks
5	不透水性 Water impermeability	（23±2）℃，相对湿度大于50% （23±2）℃，Relative humidity greater than50% 水面高度20mm Water surface height: 20mm 试验时间24h Test duration: 24 hours	无湿痕和水滴 No moisture marks and water droplets
	以下空白 The following is blank.		
备注 Comment	（此处空白This field is blank.）		

本报告结束
End of the report

注 意 事 项
Precautions

1. 本报告无“检验检测专用章”或检验检测单位公章和骑缝章无效。
The report is invalid without testing monopoly seal or inspection and testing unit official seal and paging seal.
2. 本报告涂改、部分复制无效。
The report is invalid if altered or partially copied.
3. 本报告无主检/编报、审核、批准人签字无效。
The report is invalid without the signature of inspector/editor, Reviewer and approver.
4. 对本报告若有异议，应于收到本报告之日起十五日内向本公司提出，逾期恕不受理。
Any objection to this report shall be lodged with us within 15 days from the date of receipt of the report. Overdue objection will not be accepted.
5. 本检验结果仅对受检样本/样品的本次检验有效。
The test results are only limited to the submitted sample.
6. 中英文对照时，以中文报告为准。
When comparing Chinese and English reports, the Chinese version shall prevail.

和顺路1号（场所一）地址：江苏省苏州市工业园区娄葑和顺路1号。
Address of No.1 Heshun Road (Site 1): No.1 Heshun Road, Loufeng Street, Industrial Park, Suzhou City, Jiangsu Province.
吴江同里 （场所二）地址：江苏省苏州市吴江区同里镇北联村江苏省吴江现代农业示范园区中心路5号门。
Address of Wujiang Tongli (Site 2): No. 5 Gate, Central Road， Wujiang Modern Agricultural Demonstration Park，Beilian Village，Tongli，Wujiang，Suzhou，Jiangsu Province.
吴中区（场所三） 地址：江苏省苏州市吴中区善丰路9号A1栋南区。
Address of Wuzhong District (Site 3): South Area, Building A1, No. 9 Shanfeng Road, Wuzhong District, Suzhou, Jiangsu Province.
连云港（场所四） 地址：江苏省连云港市开发区云桥路68号。
Address of Lianyungang (Site 4) : No. 68 Yunqiao Road, Development Zone, Lianyungang, Jiangsu Province.

监督电话 Supervision Phone：0512-65574008

业务电话 Business Phone：0512-65332019、0512-65332034

邮编 Postcode：215122

监督邮箱 Supervision Email：glb@ctcsz.com

业务邮箱 Business Email：65332019@163.com

网址 Website：www.ctcsz.com